

General Description:

ACRYLIC SEALER UV / 071 are based on acrylic resin for a non – yellowing basecoat. It is developed to provide a good covering, good sanding ability and preserves natural colour of the wood. Because of its extended UV absorption, it provides protection to coated light sensitive substrates.

Major Uses:

Best recommended for furniture, tables, chairs doors and frames, outdoors furniture and external wood works.

Characteristics and Physical Properties:

Appearance	Opaque
Specific gravity	0.98 kg/L
Viscosity	60"
Flash point	23 ⁰ C
Non-volatile	40%
Application condition	
Air temperature	5 ~ 35 ⁰ C
Relative humidity	85% max.
Application method	Brush, Airless or Conventional spray
Recommended catalyst	Catalyst # 026
Thinner	PU Thinner 105 / 205 AR Thinner 305
Mixing/Dilution ratio (% Volume)	Base:Catalyst:Thinner 100 20 25-30
Pot life	6 – 8 hours
Drying time	
Dust free	20 – 30 min
To touch	35 – 45 min
To recoat	2 – 3 hours
Hard	24 – 36 hours
Coverage	5~7 m ² /L (90 – 120 gms/m ²)
Recoating	Minimum 30 min ~ max 3 hrs. Medium sanding with 240 / 360 sand paper is recommended before subsequent coat is needed.

Application Procedure:

The mixture ready for use, can be applied by brush, roller or spray. Surface to be painted must be free of dirt and other contaminants. In the remaking of old woods, it is imperative to remove traces of wax, dirt and other oily matter to ensure a perfect adhesion of paint. Apply 1 – 2 coats of Acrylic Sealer UV / 071.

Precautions:

- Mixing ratio should be correctly observed.
- Paint should be used within the pot life after components have been mixed together.
- Pot life decreases at high temperature.
- Bubbling due to excessive coatings within relatively short time is likely to occur in summer. 1 – 2 thin initial coat and longer recoating interval (50 – 60 min.) eliminates bubbling.
- Never leave drums of catalyst open.

Storage:

Keep away from heat fire and store in dark, cool place at a temperature below 25⁰C. Shelf life up to 12 months in closed container.

Cleaning of Tools:

All tools should be cleaned with Wash Thinner or PU Thinner # 105 as soon as possible.

Packing:

Available in 1 Usg, 20lit Pail, and 200lit Drum.

Physiological Hazards:

ACRYLIC SEALER UV / 071 does not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. ACRYLIC SEALER UV/ 071 is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advice.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.

MAS PAINTS & CHEMICAL INDUSTRY

P.O. BOX NO: 23085, SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E

TEL NO: 009716 5311777; FAX: 009716 5311330

Website : <http://www.mas-paints.com>

Email : masuae@emirates.net.ae

