

## General Description:

MAS GLAZE is based on special resin to provide an interesting decorative paint for internal surfaces. It is suitable for use in paint techniques such as glazing, streaking and marble effect.

## Recommended Usage:

Ideal for use on interior. It can be used for previously painted surface such as wooden structure, doors and frames, furniture and interior walls.

## Physical Properties:

Colour	NCS colours
Gloss	Eggshell
Specific Gravity	0.9 kg./ lit.
Viscosity	300 +/- 10 poise
Coverage	20 m <sup>2</sup> / lit.
Touch Dry	8-12 hrs.
Through Dry	36-48 hrs.
Dry to recoat	48 hours
Solids (vol %)	50
Application	brush or roller.
Thinning / cleaning	Thinner # 155

## Surface Preparation:

### New Substrates:

- New concrete should be cured at least 28 days.
- Substrate must be free from any form of contaminants.
- Apply 1 coat of MAS Masonry AR Primer as impregnating sealer.
- Level the surface with MAS PVA Wall filler and sand until smooth.
- Apply 1 – 2 coats of Semi Gloss Enamel as an intermediate coat.
- Application of MAS GLAZE as indicated in application techniques.

### Old Concrete (previously painted)

- Remove all blistered, cracked and peeled off paint from the surface.
- Glossy finish coat must be sanded.
- Apply 1 coat of Semi Gloss Enamel as an intermediate coat
- Apply coat of MAS GLAZE in any choice of application techniques.

## Woodwork:

- Sand well the surface to removed raised fibers and make sure the wood is not too damp.
- Level any unevenness on the surface and treat all cracks and holes with wood filler.
- Apply coat of Intermediate coat.
- For previously painted wood, check the state of repair of old coats and remove any pats which are flaking or not perfectly adherent.

## Typical Recommended System:

### **On wooden surface:**

Undercoat Enamel	1 coat
Stucco Filler	2 coats
Semi Gloss Enamel	2 coats
MAS GLAZE	1 coat

### **On Concrete Plaster and Gypsum:**

MAS AR Primer	1 coat
PVA Wallfiller	2 coats
Semi Gloss Enamel	2 coats
MAS GLAZE	1 coat

## **Storage:**

The product must be stored in accordance with national regulations. The product should be kept in a cool and well ventilated place, protected from heat and direct sunlight. Containers must be kept tightly closed.

## **Cleaning of Tools:**

All tools should be cleaned with appropriate Wash Thinner or EB Thinner # 155

## **Packing:**

Available in 500 ml, 1 litre and USG

## **Physiological Hazards:**

MAS GLAZE does not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. MAS GLAZE is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advise.

*The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.*

## MAS PAINTS & CHEMICAL INDUSTRY

P.O. BOX NO: 23085, SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E  
TEL NO: 009716 5311777; FAX: 009716 5311330

Website : <http://www.mas-paints.com>

Email : [masuae@emirates.net.ae](mailto:masuae@emirates.net.ae)

