

## General Description:

HYDROTUFF 1100 is pigmented lacquer based on surfactant free acrylic dispersion for interior and exterior wood coating. It is developed to provide a hard resistant film with excellent abrasion and high flexibility and environment-friendly.

## Major Uses:

It is best recommended for coating floor surfaces, furniture, turn pieces, bamboo canes and the like. HYDROTUFF 1100 is available in satin to glossy finish which gives an excellent smoothness and opacity.

## Advantages:

- Excellent hardness
- Non –toxic / Environment – friendly.
- Easy to clean and fast drying

## Characteristics and Physical Properties:

Appearance	White & Pigmented
Specific Gravity	1.20 kg/L
Viscosity (25° C, FC # 4)	80-100 Sec.
Gloss	10/30/50/80
Application Condition: Air temperature Relative humidity	5 ~ 35°C 85% max.
Application Method	Brush, Conventional or Automatic Spray
Drying time : Dust free To touch Piling up	20-30 min. 45-60 min. 24-36 hrs.
Coating rate	8-10 m <sup>2</sup> /L (coverage will vary depending on the porosity of the surface)
Recoating	Two (2) coats may be sufficient for ordinary finish, allow 2 hrs. Drying time between coats. Light sanding with 400~600 grit sandpaper is recommended before subsequent coat when recoating time exceeds 8 hours and remove traces of wax.

## Application Procedure:

- The mixture is ready for use and can be applied by brush or spray. Surface to be coated must be free of dirt and other contaminants. In the remaking of old woods, it is imperative to remove traces of wax, dirt and other oily matter to ensure a perfect adhesion of paints
- First coat can be diluted with 5-10% with clean demineralised water, and allow to dry for an hour before sanding to remove any raise grain.
- Ensure that HYDROTUFF 1100 is applied uniformly and never leave unsealed surface to avoid moisture.

## Storage:

Store in the dark, cool and dry places. Shelf life up to 15 months in closed container.

## Chemical Resistance:

HYDROTUFF 1100 has a good resistance without additives. It is resistant to chemical agent from Level 1-B DIN 68861 part 1. HYDROTUFF 1100 does not contain heavy metal and therefore, it can be use for toys in accordance with European Std'd EN 71-3 for Toy Security.

## DRYING

The drying room temp. should not be lower than 15°C and the humidity must be less than 85°C. If the condition is beyond the required temperature, the possibility having a smooth film and less chemical resistance. It is recommended for a good dry by force drying w/o humidity starting from normal temp. up to 30°C.

## PILING

Due to the thermoplasticity of the water-based resin, piling is delicate that may result to a different effect. However, force drying plus Catalyst will improve the risk of piling.

## Packing:

Available in 1Usg. and 5 Usg. Pail

## Physiological Hazards:



See Safety Indication Sheet.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.

## MAS PAINTS & CHEMICAL INDUSTRY

P.O. BOX NO: 23085, SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E

TEL NO: 009716 5311777; FAX: 009716 5311330

Website : <http://www.mas-paints.com>

Email : [masuae@emirates.net.ae](mailto:masuae@emirates.net.ae)

