



NC PRIMER # 041 BLACK

General Description:

A pigmented nitrocellulose blended with modified alkyd resins and selected fillers. It is formulated to give a high covering property, good sanding ability and excellent elasticity.

Major Uses:

NC PRIMER # 041 BLACK can be used for all type of wooden furniture, chairs, turned pieces, clothes – hooks, picture moulding and related products.

Characteristics and Physical Properties:

| | |
|------------------|----------------------------|
| Appearance | Black |
| Sp. Weight | 1.10 kg. / lit. + / - 0.02 |
| Flash Point | 21 ⁰ C |
| Solids by Weight | 46% |
| Solids by Volume | 28% |
| Viscosity | 50 – 300 poise. |
| Coverage/ Coat | 8–9 m ² / lit. |

Method of Application:

By spraying (3- 4 atm) / brushing

- For all woods; 1 – 2 coats thinned at 40% NC Thinner.
- For woods with deep grains; 2 – 3 coats thinned at 100% NC Thinner.
- Sand the surface well with manual sanding or automatic sanding machine.

Drying Time:

| | |
|--------------|--------------|
| Dust free | 10 min. |
| Hard Dry | 3 hrs. |
| Set To Touch | 20 - 25 min. |
| Pilling Up | 12 hrs. |

Storage:

Keep material in a cool place below 25⁰C. Keep the container tightly closed. Shelf life of 12 months minimum.

Cleaning of Tools:

All tools should be cleaned with Wash Thinner or NC Lacquer Thinner as soon as possible.

Packing:

Available in USG, 5USG (Pail) and 200 ltr (Drum)

Physiological Hazards:

NC PRIMER # 041 BLACK does not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. NC PRIMER # 041 BLACK is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advice.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.

MAS PAINTS & CHEMICAL INDUSTRY

P.O. BOX NO: 23085, SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E

TEL NO: 009716 5311777; FAX: 009716 5311330

Website : <http://www.mas-paints.com>

Email : masuae@emirates.net.ae

