



# NC SEALER # 721 CLEAR

## General Description:

A transparent sanding sealer of high quality based on nitrocellulose, modified alkyds and plasticizers. Used for filling and levelling wood surfaces where transparency is required. It has a very good body to over – spraying and wetting well the structure of the wood.

## Major Uses:

NC SEALER 721 CLEAR is best for furniture in general, chairs, turned pieces and related products.

## Characteristics and Physical Properties:

Appearance	Yellowish opalescent
Sp. Gravity	0.95 kg/L
Flash Point	20 <sup>0</sup> C.
Solids by Weight	36%
Solids by Volume	34.5%
Viscosity	400 - 500 poise.
Coverage	6 ~ 8 m <sup>2</sup> / lit.
Dilution	100 – 150%
Thinner	NC Thinner # 215 / 115
<b>Drying Time:</b>	
Touch Dry	10 – 15 min.
Hard Dry	4 hrs.
Sandable	20 – 25 min.

## Method of Application:

- Apply the desired dyed or stains (optional)
- Spray 1-2 coats of NC Sanding Sealer 721 or more depending on the texture of the substrate cross – sectional.
- Sand it properly by manual or automatic sanding machine using 180 – 200 grit sand paper.

- To fill deep grains, use wood putty filler (refer to technical data for colour range.)
- Repeat the same process prior to topcoating.

Method of Application: By Trowel and Conventional Spray

Spray Data	
Conventional Spray	
Nozzle Orifice	2 – 3mm.
Nozzle Pressure	43 – 57 psi.
Dilution	50 – 100 %
Thinner	215 / 115

## Storage:

Keep material in a cool place below 25<sup>0</sup>C. Keep the container tightly closed. Shelf life of 12 months minimum.

## Cleaning of Tools:

All tools should be cleaned with Wash Thinner or NC Lacquer Thinner as soon as possible.

## Packing:

Available in 1 usg, 5usg, and 200lit. Drum.

## Physiological Hazards:

NC SEALER 721 CLEAR does not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. The mixture, in its liquid state is flammable and harmful if swallowed. If contact with eyes occurs, cleanse with fresh water and seek immediate medical advice.

*The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.*

## MAS PAINTS & CHEMICAL INDUSTRY

P.O. BOX NO: 23085, SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E

TEL NO: 009716 5311777; FAX: 009716 5311330

Website : <http://www.mas-paints.com>

Email : [masuae@emirates.net.ae](mailto:masuae@emirates.net.ae)

