

General Description:

PU LV MATT # 5390 is a VOC compliant pigmented topcoat based on poly – functional saturated polyesters and selected pigments. It is formulated for interior and exterior application to give an excellent satin finish with good covering properties. It conforms within the maximum limit of Annex II, Phase II, Table A of European Directive 2004/42/CE: 2004.

Major Uses:

PU LV MATT # 5390 is excellent for wood furniture, cabinets, bed sets, interior doors and frames.

Advantages:

- For interior/exterior application.
- Excellent hardness.
- Excellent weather/water resistance.
- Good adhesion and abrasion properties

Characteristics and Physical Properties:

Appearance	Liquid pigmented
Colour	White
Specific weight	1.25 kg/L
Viscosity (FC # 4 @25°C)	60 – 75"
Flash point	20°C
Non-volatile (%wt.)	60 +/- 0.5
Gloss (60°)	10 / 20 / 30
Application condition: Air temperature Relative humidity	5 ~ 35°C 85% maximum
Application method	Automatic or Conventional Spray
Recommended catalyst	PU Catalyst LV/13
Thinner	PU Thinner # 105/205
Mixing/Dilution ratio (Visc: 13~15" FC # 4)	Base:Catalyst: Thinner 100 : 50 : 20-25
Pot life (25°C)	2 – 3 hours
Drying time: Dust free To touch Recoat hard	15 – 17 min 45 – 60 min 2 – 3 hours 24 – 36 hours
Hardness	4H
Coating rate	6 – 8 m ² /L
Basecoat	PU Primer LV/253 and Plastofil 350

Method of Application:

- The surface to be coated should be primed with PU or Polyester Primer.
- It should be cleaned, well – sanded and free from dust, oil, water and other contaminants.
- To a well-prepared surface, apply 1 – 2 coats of PU LV MATT# 5390 horizontally and vertically
- PU LV MATT # 5390 when applied by curtain coater, the viscosity of the lacquer should be controlled and monitored for the continuity of the finish. Thinners should be added at pre-set periods to compensate the loss of solvent due to evaporation during application.
- One coat may be sufficient for ordinary finish; however, one additional coat can be applied wet on wet if necessary. Light sanding with 400~600 grit sand paper is recommended before subsequent coats, when recoating time exceeds 3 hours.

Storage:

Shelf life 12 months minimum if stored below 25°C.

Packing:

Available in 1USG, 20 li. Pail and 200 li. Drum.

Cleaning of Tools:

All tools should be cleaned with Wash Thinner or PU Thinner # 105.

Physiological Hazards:

PU LV MATT # 5390 and Catalyst LV/13 does not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. PU LV MATT # 5390 is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advice.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.

MAS PAINTS & CHEMICAL INDUSTRY

P.O. BOX NO: 23085, SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E

TEL NO: 009716 5311777; FAX: 009716 5311330

Website : <http://www.mas-paints.com>

Email : masuae@emirates.net.ae



Management System
ISO 9001:2015
ISO 14001:2015
OHSAS 18001:2007
www.tuv.com
ID 910865065

